

In 2003, Professor Youngblood joined the School of Materials Engineering at Purdue University. Promoted to Associate Professor in 2009 and Professor in 2015, he uses his polymer expertise to investigate nanotechnology, surface science, advanced processing and biomaterials. Of late, he has been specifically interested in ceramic processing using methods similar to those for polymeric materials, composites and fabrication, sustainability of materials, cellulose nanocomposites, cementitious materials, Additive Layer Manufacturing (3D printing), and durable anti-ice coatings.

# Sustainable Nanotechnology

Sustainable nanotechnology in the Youngblood group is primarily focused on cellulose nanomaterials (CN), which are sustainable, non-toxic, high strength, high stiffness, and derived from biomass. These materials are comprised of Cellulose Nanocrystals (CNCs) – rod-like liquid crystalline particles of 100nm length and Cellulose Nanofibrils (CNFs) – flexible fibrils of microns in length. Research into CNC and CNF spans new materials, new processing methods and fundamental property determination.

# **Advanced Ceramic Processing**

Professor Youngblood's ceramic research focuses on structure-propertyprocessing relationships of ceramic materials. In particular, we are investigating novel processing approaches for forming (ballistic and high temperature) ceramics and cements into complex shapes using powderpolymer suspensions as well as preparing transparent ceramic via alignment of  $\alpha$  -alumina platelets for armor applications.

# **Functional Materials**

Functional Materials research in the Youngblood group seeks to create and investigate materials, additives and components that are "active" in some way – chemically, electrochemically, thermally, etc. The application fields can span the gamut of cement, batteries, polymer additives, anti-ice coatings and others.

#### **SUSTAINABLE FLAME**

# **CNC AND CNF PROCESSING**

#### i.) Fiber Spinning


Commercially available fiber spinning methods are being explored to produce high strength, high stiffness nanocellulose reinforced commodity polymer fibers where nanoparticle alignment and nanoparticle concentration are crucial to performance. We shown that CNC and CNF addition can increase modulus and strength of the fibers and can also add as a crystallinity nucleant.

ii.) Roll to Roll (R2R) Continuous Fabrication A large-scale continuous manufacturing process for cellulose nanocrystal (CNC) and CNC composite coatings on a flexible substrate was developed in this work. In microgravure R2R, the coating thickness (from 2µm to 6µm) and CNC alignment can be controlled via process parameters and ink viscosity. Such processing is useful for producing barrier films to prevent oxygen, CO<sub>2</sub> and water transmission for food packaging and anti-bleed layers for printing.

# **NEW COMPOSITES**

#### i.) Laminates


Laminates are made up of stacked layers of bio-friendly cellulose



Polyvinyl alcohol/CNC Fibers



*Polylactic acid/CNC Fibers* 



CNC R2R coating on PET film

20 bilayer CNF


laminate structure

# 200 µm

# **AQUEOUS BASED CERAMIC-POLYMER PROCESSING**

#### i.) Additive Manufacturing

Current bulk ceramic forming processes are limited to simple structures or require secondary machining to add intricate features. Additive Manufacturing (AM) can be used with aqueous ceramic-polymer suspensions with tailored rheological properties to produce complex geometries. Presently, we are developing ceramic suspensions from different ceramic systems ( $B_4C$ ,  $Al_2O_3$ ,  $Si_3N_4$ ,  $ZrB_2$ ) for use in AM.




*3D printing of a boron carbide slurry* 

3D printed sintered boron carbide part


### ii.) Room-Temperature Injection Molding


By tailoring flow properties of aqueous ceramic-polymer suspensions, injection molding can be accomplished at room temperature to produce samples with complex geometries. Combined with pressureless sintering, this results in parts with high relative densities and mechanical properties comparable to samples prepared by traditional forming methods.



# RETARDANTS


Halogenated flame retardants (HFRs) are used in a variety of polymer systems. However, there is currently concern about their negative effects on health and the environment as bioaccumulation of HFRs in humans can lead to a variety of health issues. The goal of this project was to develop and study biologically-sourced chemicals as alternative FRs based on biomimetic design.





# **ADVANCED POLYMER COMPOSITES**

Cured-in-place pipe (CIPP) is the resin saturated fabric liner that is installed into a deteriorated pipeline and then cured using steam, hot water or UV Light. Our goal is to analyze possible environmental effect during, and after installation of cured-in-place pipe (CIPP).





nanofibrils (oxidized CNF or mechanically fibrillated CNF) as the primary component with the addition of a thermoplastic polymer binder layer to achieve high strength, transparency and toughness.

#### ii.) Nanocomposites

CNC and CNF are potential ·additives and fillers for various polymer systems where it can act as a structural reinforcement, promote nucleation, and enhance thermal, mechanical and transport barrier properties.



CNF laminates are highly transparent




CNC Epoxy nanocomposites show good dispersion

## **FUNDAMENTAL PROPERTY MEASUREMENT**

#### i.) Optical Birefringence for Anisotropy Measurement

Birefringence has been investigated for the determination of crystal orientation of a CNC film. The prime focus of our study is to establish a simple and low cost experimental technique using a standard UV-Vis spectrometer to determine the order parameter (S) for both isotropic and anisotropic configurations. The transmitted light intensity of CNC films between cross polarizers for the bright and dark fields were measured to determine the linear dichroitic ratio, which were used to calculate the order parameters of different crystalline arrangements.




# **STRUCTURED MATERIALS**

5 min t = 1 minInjection molding of alumina slurry.

#### **Transparent Ceramics**

Current methods for producing transparent ceramics involve extremely high sintering temperatures and/or complex and very large magnetic fields to align ceramic particles. By compression-molding a mixture of platelet-grain alphaalumina in a thermoplastic polymer, a high degree of crystallographic alignment can be achieved. Subsequent binder burnout and densification will yield a dense, transparent, polycrystalline ceramic.



Platelet-grained alumina

Shadow visible behind hot-pressed alumina

#### **3D** Printing Cement with Controlled Architecture


Additive manufacturing offers unique opportunities to design and test architectured cement-based materials. We have shown that "Bouligand" architectures with a pitch angle of 45° demonstrate a higher specific strength than cast specimens over a wide range of porosity. As well, we have shown that some architectures can provide flexibility, much higher toughness, and Mutliphasic mixture of VOCs, water, and partially cured polymer are released to the environment during steam curing of CIPP.

# **SUSTAINABLE MATERIALS FOR ENERGY STORAGE**

Sustainable energy sources need storage solution to reduce intermittency and provide stable power. However, current electrochemical storage are either too expensive or have to low capacity for such use. Here we investigate earth abundant materials such as biomass, sulfur and common metals such as sodium integrated with processing to lower cost.









#### ii.) Hygroscopic Swelling of CNC Films


Hygroscopic swelling is commonly characterized by the coefficient of hygroscopic swelling (CHS), which correlates the degree of expansion of a material to the mass intake of water as a function of humidity. CHS of selforganized and shear-oriented CNC films was determined by capturing hygroscopic strains produced by water vapor intake in equilibrium. Here, we use contrast enhanced microscopy digital image correlation (CEMDIC) to determine CHS as a function of CNC alignment.



crack deflection in brittle cementitious materials.



structure, d. double-modulus cement "spring", e. Bouligand structure with 8 degree twist. Bottom: MOR vs density curve showing 3D printed architectures show anomalous strength behavior.



a. Waste biomass such as pistachio shell can be carbonized and used for batteries. b. Performance depends on carbonization temperature.

# **ADDITIVES FOR CEMENTITIOUS MATERIALS**

CNCs reduce cement paste yield stress, yet improve degree-of-hydration (DOH) all at very low dosages. Lowered yield improves workability, while increased DOH increases strength. We are investigating the origin of these observations and how to improve CNC performance. We are now trying to apply CNC additives at the macro level during field tests.

